



Designation: B 101 - 02

Standard Specification for Lead-Coated Copper Sheet and Strip for Building Construction¹

This standard is issued under the fixed designation B 101; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This specification establishes the requirements for lead-coated copper sheet and strip in flat lengths (or in coils) in ounce-weight thicknesses for roofing, flashing, gutters, downspouts, and for the general sheet metalwork in building construction. The lead coating is applied by hot dipping.

1.2 Materials made to this specification are not intended for electrical applications.

1.3 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units, which are provided for information only and are not considered standard.

Note 1—A companion specification for copper sheet and strip for building construction is Specification B 370.

1.4 The following hazard caveat pertains to the test method portion, Section 17, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 The following documents in the current issue of the *Annual Book of ASTM Standards* form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:

B 248 Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar²

B 370 Specification for Copper Sheet and Strip for Building Construction²

D 601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast²

B 846 Terminology for Copper and Copper Alloys²

E 8 Test Methods for Tension Testing of Metallic Materials³

E 37 Test Methods for Chemical Analysis of Pig Lead⁴

E 46 Test Methods for Chemical Analysis of Lead- and Tin-Base Solders⁵

E 62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)⁴

B 112 Test Methods for Determining Average Grain Size³

E 478 Test Methods for Chemical Analysis of Copper Alloys⁶

3. General Requirements

3.1 The following sections of Specification B 248 constitute a part of this specification:

3.1.1 Significance of numerical limits,

3.1.2 Inspection,

3.1.3 Rejection and reheating,

3.1.4 Certification,

3.1.5 Mill test reports, and

3.1.6 Packaging and package marking.

4. Terminology

4.1 For definitions of terms related to copper and copper alloys, refer to Terminology B 846.

4.2 *Definitions of Terms Specific to This Standard*:

4.2.1 *coil*—a length of the product wound into a series of connected turns.

4.2.1.1 *Discussion*—The unqualified term “coil” as applied to “flat product” usually refers to a coil in which the product is spirally wound, with the successive layers on top of one another. (Sometimes called a “roll.”)

4.2.2 *lead-coated copper sheet (for building construction), n*—a rolled flat product over 24 in. (610 mm) in width and of ounce-weight thickness from 8 oz (227 g) to 48 oz (1361 g).

4.2.3 *lead-coated strip (for building construction), n*—a rolled flat product up to and including 24 in. (610 mm) in width and of ounce-weight thickness from 8 oz (227 g) to 48 oz (1361 g).

¹ This specification is under the jurisdiction of Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved Apr. 10, 2002. Published June 2002. Originally published as B 101 - 35 T. Last previous edition D 101 - 01.

² *Annual Book of ASTM Standards*, Vol 02.01.

³ *Annual Book of ASTM Standards*, Vol 03.01.

⁴ *Annual Book of ASTM Standards*, Vol 03.05.

⁵ Discontinued, see 1994 *Annual Book of ASTM Standards*, Vol 03.05.

⁶ *Annual Book of ASTM Standards*, Vol 03.06.

*A Summary of Changes section appears at the end of this standard.

B 101

4.2.4 *lengths, mill, n*—straight lengths, including ends, that are conveniently manufactured in the mills.

4.2.4.1 *Discussion*—Full length pieces are usually 8, 10, or 12 ft (2.44, 3.05, or 3.66 m) and subject to established length tolerances.

4.2.5 *lengths, specific, n*—straight lengths that are uniform in length, as specified, and subject to established length tolerances.

4.2.6 *ounce-weight*—the weight of uncoated copper sheet or strip expressed in ounces per square foot.

4.2.7 *thickness, ounce-weight, n*—the metal thickness that corresponds to the ounce weight.

5. Ordering Information

5.1 Include the following information:

- 5.1.1 ASTM designation and year of issue.
- 5.1.2 Temper (Section 8 and Table 1),
- 5.1.3 How furnished: flat lengths or in coils,
- 5.1.4 Quantity: total weight or sheets of each size,
- 5.1.5 Ounce-weight or ounce-weight thickness of the uncoated copper sheet or strip (Table 2),
- 5.1.6 Dimensions: width and length (Section 12),
- 5.1.7 Certification, where required (see 5.1.4),
- 5.1.8 Mill test report, where required (see 5.1.5), and
- 5.1.9 If the material being purchased is intended for use by agencies of the U.S. government, refer to Section 11.
- 5.1.10 Other variations in coating or texture shall be furnished by agreement in writing between the purchaser and the manufacturer or supplier.

6. Materials and Manufacture

6.1 *Materials:*

- 6.1.1 The lead coating shall conform to the chemical requirements of Table 3.
- 6.1.2 The copper sheet or strip to be lead coated shall be manufactured by any process that provides a finished product that conforms to the requirements of Specification B 370.

6.2 *Manufacture:*

- 6.2.1 The lead coating shall be applied to the copper sheet or strip by hot dipping in a bath of molten lead.
- 6.2.2 Unless otherwise specified, the lead coating shall be applied to the copper sheet or strip after slitting and cutting to the specified length.

7. Chemical Composition

- 7.1 The copper sheet or strip shall have a minimum copper, including silver, content of 99.5 %.
- 7.2 Any copper that complies with 7.1 shall be acceptable.

TABLE 2 Sheet Weights

Nominal Weights and Thickness of Bare Copper Sheets		Minimum Weight of Lead-Coated Copper Sheet
Ounce-Weight, oz/in ²	Ounce-Weight Thickness ^a , in. (mm)	oz/in ² (g/cm ²)
24	0.0323 (0.820)	24.6 (7580)
20	0.0270 (0.688)	21.0 (6405)
16	0.0216 (0.549)	17.0 (5185)
12	0.0162 (0.411)	13.0 (3960)

^aBased upon a density of 0.322 lb/in.³ (8.91 g/cm³).

TABLE 3 Chemical Requirements for Lead Used to Coat Copper Sheet

Element	Composition, max. %
Silver	0.02
Copper	0.08
Arsenic plus antimony	0.10
Zinc	0.005
Iron	0.01
Bismuth	0.08
Lead	remainder
Tin	3.0-4.0
Phosphorus	0.03

7.3 If limits for unnamed elements are required, they shall be established and analysis required by agreement between manufacturer or supplier and purchaser.

7.4 The lead coating shall conform to the chemical requirements of Table 3.

8. Temper

8.1 Uncoated copper sheet and strip covered by this specification is commercially available in the following tempers, as defined by Classification B 601: O60 (soft annealed); H00 (eight hard, cold-rolled); and H01 (quarter hard, cold-rolled high yield) (see Table 1).

9. Physical Property Requirements

9.1 Although no minimum grain size is specified for soft-temper material, it shall be fully recrystallized.

10. Mechanical Property Requirements

10.1 *Tensile Strength Requirements:*

10.1.1 The uncoated product furnished under this specification shall conform to the tensile requirements prescribed in Table 1 when tested in accordance with Test Methods B 8. Tension test specimens shall be taken so that the longitudinal axis of such specimens is parallel to the direction of rolling.

TABLE 1 Mechanical Properties of Uncoated Sheet

Temper Designation		Tensile Strength, ksi ^a (MPa)		Yield Strength, at 0.5 % Extension Under Load, min, ksi (MPa)	Approximate Rockwell Hardness ^b (for Information Only)			
Standard	Former	Min	Max		F Scale		Superficial 30 T	
					Min	Max	Min	Max
O60	soft	30 (210)	38 (265)	65	...	31
H00	cold-rolled	32 (225)	40 (280)	20 (140)	54	82	15	49
H01	cold-rolled (high yield)	34 (240)	42 (295)	28 (195)	60	84	16	51

^aksi = 100 psi.

^bRockwell hardness values apply as follows: The F scale applies to metal 0.020 in. (0.508 mm) and over in thickness; the superficial 30T scale applies to metal 0.012 in. (0.305 mm) to 0.020 in. (0.508 mm) in thickness.

B 101

10.2 Rockwell Hardness:

10.2.1 The approximate Rockwell hardness values given in Table 1 are for general information and assistance in testing and shall not be used as a basis for product rejection.

Note 2.—The Rockwell hardness test offers a quick and convenient method of checking for general conformity to the specification requirements for temper and tensile strength.

11. Purchases for the U.S. Government

11.1 When specified in the contractor purchase order, product purchased for an agency of the U.S. government shall conform to the special government requirements specified in the Supplementary Requirements section of Specification B 248.

12. Dimensions, Mass, and Permissible Variations

12.1 *Weight*—The weight of the lead-coated sheet and strip copper shall conform to the minimum requirements of Table 2.

12.2 *Width*—The tolerances for width of sheets shall be as shown in Table 4.

12.3 *Length*—Sheets ordered in exact lengths shall be permitted to have a variation of $\pm 1/4$ in. (+6.5 mm) in length.

12.4 *Straightness*—The tolerances on straightness or edge-wise curvature (depth of arc) in any 72-in. (2-m) portion of the total length shall be as specified in Table 5 for slit metal and Table 6 for square-sheared metal.

13. Workmanship, Finish and Appearance

13.1 Lead Coating:

13.1.1 The lead coating shall uniformly cover both surfaces, edges, and ends.

13.1.2 The coating shall be smooth and free from pinholes, voids, or unwetted areas, but bloomishes of a nature that do not interfere with the intended application are acceptable.

13.1.3 The weight of the lead coating shall conform to the requirements of Table 7.

14. Sampling

14.1 Refer to Specification B 248 for chemical and mechanical properties.

14.2 Weight of Coating Tests:

14.2.1 *Method A*—Test ten sheets selected at random.

14.2.2 *Methods B and C*—Test four representative samples cut from the diagonal of one sheet selected at random.

15. Number of Tests and Retests

15.1 Tests:

15.1.1 Refer to the section of Specification B 248 for chemical and mechanical tests.

15.1.2 A test on each specimen taken in 14.2.1 or 14.2.2, as applicable, shall be made for the determination of lead.

15.2 Retests:

TABLE 4 Width Tolerances

Width, in. (mm)	Tolerances, in. (mm)
6 (125) and under	± 0.025 (0.6) - 0
Over 6 - 14 (125-355), incl	± 0.050 (1.2) - 0
Over 14 (355)	± 0.125 (3.2) - 0

TABLE 5 Straightness Tolerances for Slit Metal

Width, in. (mm)	Straightness Tolerance, in. (mm)
Over 4 to 24 (102 to 610), incl	$1/32$ (0.8)

TABLE 6 Straightness Tolerances for Square-Sheared Metal

Note 1.—Maximum edgewise curvature (depth of arc) in any 72-in. (1.83-m) portion of the total length (not applicable to metal over 120 in. (3.05 m) in length).

	Straightness Tolerances, in. (mm)	
	Up to 10 in. (254 mm) Incl. in Width	Over 10 in. (254 mm) in Width
All thicknesses	$1/32$ (0.8)	$1/16$ (0.6)

TABLE 7 Weight of Lead Coating, lb (kg)^a

Min	Max
12 (5.4)	16 (7.3)

^aThe weight of coating specified is the total weight of lead applied to two sides of 100 ft² (9.3 m²) of copper sheet, approximately one half of the coating to be on each side of the sheet.

15.3.1 When a specimen fails to meet the requirements of a test, one retest shall be made under the conditions of the original test.

15.3.2 All specimens must conform to test requirements when retested or the material may be rejected.

16. Specimen Preparation

16.1 Refer to Specification B 248 for the chemical and mechanical property test specimen preparation.

16.2 Weight of Coating Tests:

16.2.1 Refer to 17.4.1 of this specification for Method A.

16.2.2 Refer to 17.4.2 of this specification for Method B.

16.2.3 Refer to 17.4.3 of this specification for Method C.

17. Test Methods

17.1 Chemical Composition:

17.1.1 Chemical composition, in case of dispute, shall be determined as follows:

Element	Range, %	Test Method
Copper	99.0 min	E 478
	0.001 to 0.1	E 37
Lead	95.0 to 100	by difference
	0.001 to 0.02	E 37
Tin	1 to 4	E 46
	0.001 to 0.03	E 37
Arsenic	0.0005 to 0.02	E 37
	0.001 to 0.03	E 37
Antimony	0.001 to 0.009	E 37
	0.0005 to 0.009	E 37
Zinc	0.002 to 0.2	E 37
	0.001 to 0.03	E 62

17.1.2 Test method(s) used for the determination of element(s) required by contractual or purchase order agreement shall be agreed upon between the manufacturer and the purchaser.

17.2 *Grain Recrystallization*—Recrystallization shall be determined in accordance with Test Methods E 112.

17.3 Mechanical Requirements:

17.3.1 *Tensile Strength*—Tensile strength shall be determined in accordance with Test Methods E 8.

ASTM B 101

17.3.2 *Yield Strength*—Yield strength shall be determined at 0.5 % extension-underload of Test Methods E 8.

17.3.3 Test results are not seriously affected by variations in speed or testing. A considerable range of testing speed is permitted; however, the rate of stressing to the yield strength should not exceed 100 ksi/min. Above the yield strength, the movement per minute of the testing machine head under load should not exceed 0.5 in./in. of gage length (or distance between grips for full-section specimens).

17.4 *Weight of Coating Test*—When testing is specified, the determination of the lead coating shall be made in accordance with one of the three following methods:

17.4.1 *Method A*—Select at random ten sheets from those being coated. Weigh these ten sheets before and after coating and calculate the weight of the coating from the difference in weight on the basis of the ordered size.

17.4.2 *Method B*—Select at random one sheet from the lead-coated sheets furnished. Cut four representative samples 2¼ by 2¼ in. (60 by 60 mm) from each sheet, uniformly spaced along a diagonal, the end samples being taken not less than 1 in. (25 mm) from the edge. Weigh and then completely dissolve the four samples of sheet obtained. Determine the copper by electrolytic assay in accordance with Test Method E 478. Calculate the weight of the lead coating as the difference between the total weight of the samples and the weight of copper found.

17.4.3 *Method C*—Select at random one sheet from the lead-coated sheets furnished. Cut four representative samples

2¼ by 2¼ in. (60 by 60 mm) from the sheet, uniformly spaced along a diagonal, the end samples being taken not less than 1 in. (25 mm) from the edge. After removing the burrs, clean each sample and rinse with alcohol and ether. Obtain the weight of the specimens and the weight of the coating from measurements taken of the specific gravity or density of these samples as determined by the usual method of weighing in air and in water.

17.4.4 Calculations are as follows:

$$\text{Weight of lead coating, lb/100 ft}^2 = (29.1 - 259/D)W \quad (1)$$

$$\text{Weight of bare copper sheet, oz/ft}^2 = (41.5/D - 3.66)W \quad (2)$$

where:

- W = weight of the sample in air, g;
- D = density of the sample = $(W \times D_1)/(W - M)$;
- D_1 = density of water at room temperature; and
- M = weight of the sample in water, g.

Note 3—To convert lb/100 ft² to kg/m², multiply by 0.0488. To convert oz/ft² to kg/m², multiply by 0.305.

17.4.5 In case of dispute, the weight of the coating shall be determined by Method B.

18. Keywords

18.1 building construction; downspouts; flashing; lead-coated copper sheet and strip; roofing; sheet metal-sheet strip in flat lengths/coils for building construction

SUPPLEMENTARY REQUIREMENTS

Refer to the section on Supplementary Requirements in Specification B 248.

APPENDIX

(Nonmandatory Information)

XI. METRIC EQUIVALENTS

XI.1 The SI unit for strength properties now shown is in accordance with the International System of Units (SI). The derived SI unit for force is the newton (N), which is defined as that force that, when applied to a body having a mass of one kilogram, gives it an acceleration of one metre per second squared ($N = \text{kg}\cdot\text{m}/\text{s}^2$). The derived SI unit for pressure or

stress is the newton per square metre (N/m^2), which has been named the pascal (Pa) by the General Conference on Weights and Measures. Since 1 ksi = 6 984 757 Pa, the metric equivalents are expressed as megapascals (Mpa), which is the same as MN/m^2 and M/mm^2 .



B 101 SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B 101 - 01) that may impact the use of this standard.

(1) Revised values for minimum weight of lead-coated copper sheet in Table 2. Other tables are unchanged.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2850, United States. Individual reports (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9665 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).